



## TECHNICAL INFO

Compounds	- ammonium bifluoride in flakes - low content of barium - stabilizers
Working density	1,36/1,388 kg/lt
Working temperature	20° C
Washability	Easily washable
Consumption	1,34 gr/dm <sup>2</sup>
Result of etching	With 15 seconds dipping: 7/8 Rz Velvety to the touch and uniform structure  With 35/40 seconds dipping: 12/13 Rz rough to the touch and uneven structure
Composition	With acid HF 40% or acid HCL 32/33%

### SAPI IMPIANTI S.r.l.

Zona Industriale Loc. Il Piano - 53031 - Casole d'Elsa - Siena (Italy)  
Tel. +39 0577/949110 - Fax +39 0577/947828 - info@sapi-impianti.it - www.sapi-impianti.com